## **Technical Information**

TI/N-CPN/IP Plastomoli® DOA May 2023

Page 1 of 3

Supersedes edition dated August 2022

## Petrochemicals Plasticizers



# Plastomoll® DOA

Plasticizer for PVC, surface coatings and rubber. Especially suited for flexible PVC colorants and coatings requiring good low-temperature properties. Plastomoll® DOA meets the requirements for good packaging and can, therefore, be used for flexible PVC films for food contact (cling film).

Chemical Nature Dioctyl adipate

BASF Registered Name Plastomoll® DOA

**CAS No.** 103-23-1

Molecular Weight 371

Formula C<sub>22</sub>H<sub>42</sub>O<sub>4</sub>

**Molecular Structure** 

**Product Specifications** 

Value Test Method Specific gravity @ 25°/25 °C **ASTM D-4052** 0.923 - 0.927 Ester content, % by weight (minimum) **ASTM D-3465** 99.6 Acid Number, mg KOH/g (maximum) 0.1 **ASTM D-1045** Water, % by weight (maximum) ASTM E-203 0.1 Color, Pt-Co Units (APHA, maximum) **ASTM D-5386** 25 Suspended Matter COLSFFM\* visual

\*Clear Oily Liquid Substantially Free of Foreign Material

### **Typical Physical Properties**

The following data were measured in the BASF Corp. laboratory. They do not represent any legally binding guarantee of properties for our sales product.

	Value
Pour point, °C	-75
Flash point (COC), °C	199
Odor	mild characteristic
Surface Tension, mN/m	30.3
Solution Temperature, °C	144
Plastisol Gelation Temperature, °C	140
Vapor Pressure @ 20 °C, mbar	< 0.01
Solubility @ 25 °C in water, mg/L	< 0.01

## Viscosity & Density Data

Temperature (°C) -40 -30 -20 -10 0 10 20 40	Dynamic viscosity (cP) 760 280 122 60.9 34.1 21.0 13.8 7.08	Density (g/cm³) 0.972 0.964 0.956 0.949 0.941 0.933 0.926 0.911
40 60	7.08 4.25	0.911 0.896
80	2.84	0.881

## Description

Plastomoll® DOA is a highly efficient plasticizer which imparts excellent low temperature flexibility and resistance to impact to the base resin. For these reasons it finds wide use in polymeric systems based on vinyl, nitrocellulose and rubber. It is extensively used in food contact applications.

In addition to its high efficiency and contribution to the low temperature properties of vinyl, Plastomoll<sup>®</sup> DOA is chemically stable and resistant to discoloration on extended exposure to heat and ultraviolet light.

The combination of low viscosity and efficiency provide excellent dry blending and processing characteristics.

# **Applications**

When used in plastisols, Plastomoll® DOA imparts low initial viscosity and good viscosity stability. The contribution to relative yield value suggests use in dip coating formulations where resistance to sag is required.

## Safety

Plastomoll® DOA does not require special handling. Handle in accordance with good industrial hygiene and safety practices. Avoid eye contact by wearing personal protective equipment. If eye contact occurs, wash with flowing water and contact physician.

Avoid repeated or prolonged skin contact. Avoid breathing vapors by providing adequate ventilation.

Always refer to the Safety Data Sheet (SDS) for detailed information on safety.

## **Storage and Handling**

Plastomoll<sup>®</sup> DOA can be stored for one year at temperatures below 40°C, if moisture is excluded.

## **Packaging**

Plastomoll® DOA is available in bulk, tank trucks or rail cars.

#### **Contact Information**

## Marketing

BASF Corporation 11750 Katy Freeway, Suite 120 Houston, TX 77079, USA

Tel: +1 800-533-8961 Fax: +1 713-759-3036 E-mail: plasticizers@basf.com

## **Technical Support**

BASF Corporation 4403 La Porte Highway 225 Pasadena, TX, 77501, USA

Tel: +1 281-884-4432 Fax: +1 281-884-4302

### Visit us online at

http://www.plasticizers.basf.com

#### Note

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© 2022 BASF Corporation